

# Study on use of Rice Husk Ash in Concrete

M. S. Rabade<sup>1</sup>, S. S. Tavaré<sup>2</sup>, V. V. Patil<sup>3</sup>, A. R. Patil<sup>4</sup>

Assistant Professor, Department of Civil Engineering<sup>1</sup>

UG Students, Department of Civil Engineering<sup>2,3,4</sup>

D. Y. Patil Technical Campus, Talsande, Kolhapur, India

**Abstract:** *The rice husk is an agricultural waste which is obtained from milling process of paddy and approximately 22% of the weight of paddy is rice husk. The waste is used as fuel in producing steam in parboiling process. The 25 % the weight of husk is converted into ash which is known as rice husk ash (RHA) and is again a waste which is disposed. This ash consists of amorphous silica which can be used as pozzolana in making concrete and cement instead of disposing it without compromising on the properties of cement or concrete if replaced in specific proportion with other constituents of cement or concrete. In this study the ordinary Portland cement is replaced in different proportion with RHA to obtain concrete with comparable and satisfactory strength and properties to that of normal concrete. The proportions of replacement chosen are at 2.5% interval starting from 5 % to 15 % and the casted concrete were tested under compression at different ages and results obtained are compared with normal concrete of same grade and it is concluded that the results are comparable.*

**Keywords:** RiceHusk Ash, Cement, Concrete, Compressive strength, Split tensile strength, RHA

## I. INTRODUCTION

The rice husk is produced in rice mill in the milling process of paddy and after the burning process of rice husk in boiler the RHA is obtained. The paddy grain is surrounded by the byproduct known as husk. In the milling process of paddy approximate 78% of weight is received as rice and 22% of weight is received as husk. The husk is used as fuel in the parboiling process for produce steam. In the firing process of rice husk, this husk has approximately 75% organic volatile substance and remaining 25% weight of husk is transformed into ash and this ash is known as rice husk ash (RHA). The RHA contains about 80-90% amorphous silica. In every 1000kg of paddy, approximate 22% (220 kg) of husk is produced, and around 78% (780 kg) of rice is produce. In the milling process when this husk is burnt in the boiler approximate 25% (55 kg) of rice husk ash is produced [1-3].

India is a major rice producing country, and the husk generated during milling is mostly used as a fuel in the boilers for processing paddy, producing energy through direct combustion and / or by gasification. About 20 million tons of RHA is produced annually. This RHA is a great environment threat causing damage to the land and the surrounding area in which it is dumped. Lots of ways are being thought of for disposing it by making commercial use of this RHA. In the present investigation, Portland cement was replaced by rice husk ash at various percentages to study compressive and flexural strength [4,5].

## II. RICE HUSK ASH (RHA) APPLICATIONS

1. Used in steel industries
2. Due to fine insulating properties of rice husk like low thermal conductivity, high melting point, low bulk density high porosity, it used for the production of high quality steel. It is also used as a coating over the molten metal in the tundish and in ladle which acts as a very good insulator and does not allow quick cooling of metal.
3. Used in cement and construction industries
4. Blended cement is produced by using rice husk ash for fulfilling the increasing need for building material. Rice husk ash is a highly reactive pozzolan. Rice husk ash mainly used a replacement of silica fume or as admixture in manufacturing of low cost concrete block
5. Use of rice husk ash as silica
6. Due to large silica content in rice husk ash, extraction of silica is economical. Silica is used in rubber

industries as a reinforcing agent, in cosmetics, in toothpastes, in food industries as an anti-caking agent. There is a growing demand for fine amorphous silica in the production of high performance cement and concrete, use in bridges, marine environments, nuclear power plants etc. Silica aerogels prepared from Rice Husk Ash (RHA) finds application in super thermal insulators, catalyst supports and dielectric materials. It can be an economically viable raw material for the production of silicates and silica.

7. Other uses

8. Indian Space Research Organization has successfully developed a technology for producing high purity silica from RHA that can be used in manufacturing of silicon chip in industry. RHA used in vulcanizing rubber. Use of Rice Husk to synthesize High-Performance Phosphors. Other uses of Rice Husk (RH) are in control of insect pests in Stored Food Stuffs. RHA has been found to be effective as an oil spill absorbent, and for use in waterproofing chemicals, flame retardants, and as a carrier for pesticides and insecticides.

### III. REVIEW OF LITERATURES

The literatures regarding the potential uses of rice husk as one of the suitable aggregates for concrete have been reviewed and are presented below.

Bertil Persson reported that on these mechanical properties, such as strength, creep, elastic modulus and shrinkage of self-compacting concrete and the corresponding properties of normal compacting concrete (NCC). The report included eight mix proportions of sealed or air-cured specimens. The water binder ratio which is used in this (w/b) varying between 0.24 and 0.80. Fifty percent of the mixes were SCC and rests were NCC. The time period at loading of the concrete mix in the creep studies varied between 2 and 90 days. The results indicated that elastic modulus, creep and shrinkage of SCC did not change significantly from the corresponding properties of NCC.

Ahmadi et al reported the development of Mechanical properties up to 180 days of self-compacting concrete and Ordinary concrete mixes with rice-husk ash (RHA), from a rice paddy milling industry. Two different replacement Percentages of cement by RHA, 10%, and 20%, and two different water/cementitious material ratios (0.40 and 0.35) were used for the self compacting and normal concrete specimens. The results were compared with those of the self compacting concrete without RHA. SCC mixes show higher compressive and flexural strength and lower modulus of elasticity rather than the normal concrete. Upto 20% replacement of cement with rice husk ash in matrix caused Reduction in use of cement and expenditures, and also improved the quality of concrete at the time period of more than 60 days. It was said that RHA provides a good effect on the Mechanical properties after 60 days

S. S. Viveket al in this paper examined the performance of Self Compacting Concrete (SCC) by replacing cement with Varying the silica fume (SF). An attempt was made to check performance and properties of fresh concrete by slump Flow test, T500 test and the hardened properties of concrete by compression test. There were four mixes of SCC made by replacement of cement with different percentages of silica fume from 5 to 20% with an increment of 5%. Tests were Carried out to assess the compressive strength of concrete at different ages namely 7, 14 and 28 days. For SCC, super-plasticizer (Complast SP430) was added in optimized dosage. It was found that replacement of cement by 10% of silica Fume with a water to powder (w/p) ratio of 0.8 gave better results on fresh properties and compressive strength of admixed concrete. The replacement of cement by 15% of silica fume with a w/p ratio of 0.8 gave better results in Slump flow and T50 test. Whereas replacement of cement by 5% of silica fume with a w/p ratio of 0.8 gave better compressive strength at the time period of 7 and 14 days but it fails in flow properties and also the replacement of cement by 10% of silica fume with a w/p ratio of 0.8 gave better fresh concrete performance and compressive strength At the time of 28 days.

Yaghuobmohammadi et al studied that the effect of silica fumes on properties of self-compacting lightweight concrete (SCLC) containing perlite and leca. For this purpose, silica fume has been replaced by different contents. In This study, all mixtures total cementitious materials (cement + silica fume) were kept at 450 kg/m<sup>3</sup>. Test was carried out such as Slum flow, L-box, U-box, V-funnel and J-ring. This research showed that mixtures without silica fume were not satisfactory. For all tests added the silica fume demonstrated acceptable values. However, for the SCLC mixture Containing 15 silica fume significant results were attained. Adding silica fume, compressive strength of samples Increased.

Krishna Murthy N. et.al reported Self-compacting concrete possesses good qualities, productivity and working Conditions due to removal of voids. Designed for self-compacting concrete mix design with 29% of coarse aggregate, replacement of cement with Metakaolin and class F fly ash, combinations of both and controlled SCC mix with 0.36 water/cement ratio and 388 liter/m<sup>3</sup> of cement paste volume. After that they introduced Metakaolin and class F fly ash were user friendly for SCC design mix, and considered to be most promising building for the revolutionary changes on Structures.

P.Padma Rao, et al studied the Use of Rice Husk Ash in Concrete, In this investigation, a feasibility study is made to Use Rice Husk Ash as an admixture to an already replaced Cement with fly ash (Portland Pozzolana Cement) in Concrete, and an attempt has been made to investigate the strength parameters of concrete. Five different replacement Levels namely 5%, 7.5%, 10%, 12.5% and 15% are chosen for the study concern to replacement method. Large range of curing periods starting from 3days, 7days, 28days and 56days are considered in this investigation. All materials shall be brought to room temperature, preferably 27<sup>o</sup>+ 30 C before commencing the results. At all the cement replacement Levels of Rice husk ash; there is gradual increase in compressive strength from 3 days to 7 days. However there is Significant increase in compressive strength from 7 days to 28 days followed by gradual increase from 28 days to 56Days.

#### **Pollution cause due to burnt clay brick**

Were found that most of the people around the bricks kiln was more concern about the soil and air pollution. People are suffering or facing breath problem, nasal problem, eye burning and other diseases. Brick kilns production of different toxic pollutant components for air pollution and human hazards. People are suffering with diseases like respiratory, nasal cognition, burning of eyes and loss of visibility, which accelerated many accidents on that particular area due to brick kilns. Some of the ash is carried by flue gases. It is possible to mix a part of the fuel in the powdered form with the clay during clay preparation. This fuel is referred as internal fuel as it is present inside the brick. As the brick is heated in the kiln, combustion of internal fuel takes place. However, in this case as the fuel particles are entrapped in the brick, the ash associated with them remains inside the brick and does not come out. This helps in reducing the pollution. Use of good quality agriculture soil in large quantities for brick making is also a grave area of concern. In geographical regions having thin topsoil, this result in reduction in the productivity of land and in extreme cases the land does not remain fit for agriculture use. To reduce this wastage some steps can be taken. At present only top surface (3 to 10 ft) is utilized for brick making, resulting in large surface area being affected due to digging of soil for brick making. So deep mining of clay can reduce the area affected due to dig of soil for brick making. All this mentioned measures would require mechanization of some of the processes in brick making. Development of suitable low cost

OBILADE, I.O. investigated the use of rice husk ash as partial replacement for cement in concrete. In this research work on the properties of Rice Husk Ash (RHA) when used as partial replacement for Ordinary Portland Cement(OPC) in concrete. OPC was replaced with RHA by weight at 0%, 5%, 10%, 15%, 20% and 25%. 0% replacement served as the control. The concrete mix proportion was 1:2:4 by weight. Compressive Strength test was carried out on Hardened 150mm concrete cubes after 7, 14 and 28 days curing in water. The concrete used in this research work was made using Binder, Sand and Gravel. The results revealed that the Compacting factor decreased as the percentage replacement of OPC with RHA increased.

Makarand Suresh Kulkarni et al studied the Effect of Rice Husk Ash on Properties of Concrete The main objective of this work is to study the suitability of the rice husk ash as a pozzolanic material for cement replacement in concrete. However it is expected that the use of rice husk ash in concrete improve the strength properties of concrete. Also it is an attempt made to develop the concrete using rice husk ash as a source material for partial replacement of cement, which satisfies the various structural properties of concrete like compressive strength and Flexural strength. From the Entire experimental work & studies it is concluded that mix M2 (M0+20% RHA) is the best combination among all mixes, which gives max, tensile, flexure & compression strength over normal concrete.

Velupillai (1997) – The use of RHA will contribute not only, to the production of concrete of a higher quality and Lower cost, but also the reduction of carbon dioxide (CO<sub>2</sub>) emissions from the production of cement. The partial replacement of cement by RHA will result in lower energy consumption associated with the production of cement.

S.RAMESH et al studied the behaviour of cement concrete with rice husk ash. In this study RHA partially replaced to 20% by weight of cement. Experimental works and studies are conducted are workability, weight comparison, compressive strength, tensile and flexural strength of concrete. This paper reported the properties, benefits and uses of RHAC by experimental works. From the experiments and test results on fresh and hardened concrete, it is concluded That it will increase the workability as compared to normal concrete. The use of rice husk ash will increase the Corrosion resistance and durability of concrete and it reduces the environmental pollution due to construction.

## II. CONCLUSION

Based on study following conclusions are drawn:

1. Use of super plasticizer is helpful in flowability and segregation control.
2. Strength of self compacting concrete using silica fume increases upto 20% replacement.
3. The use of silica is also beneficial in flowability property.
4. Use of rice husk ash results good effect on compressive strength.
5. Use of these materials are environment friendly.
6. It is also cost effective.
7. Use of GGBS also gives the better on compressive strength.

## ACKNOWLEDGEMENT

We would like to express our sincere thanks towards researchers who give us valuable information which is useful in Proposed project

## REFERENCES

- [1]. P.Padma Rao et al. (2014), A Study on Use of Rice Husk Ash in Concrete, IJEAR Vol. 4, Issue Spl-2, Jan – June 2014, ISSN: 2348-0033(Online) ISSN : 2249-4944 (Print).
- [2]. OBILADE, I.O. , USE OF RICE HUSK ASH AS PARTIAL REPLACEMENT FOR CEMENT IN CONCRETE, ISSN2305-8269, Sept. 2014. Vol. 5. No. 04
- [3]. Kartini k et al. (2008)-Improvement on mechanical properties of Rice Husk Ash concrete with Superplasticizer University TechnologyMARA, MALAYSIA ,international conference on construction and building technology ICCBT 2008 -A – (20) – pp221-230.
- [4]. Dao V et al. (2008)- Effect of rice husk ash on properties of high strength concrete the 3rd ACF International conference-ACF/VCA 2008.
- [5]. Ramezaniapour A et al. (2009)- the effect of rice husk ash on mechanical properties and durability of sustainable concret .
- [6]. Zemke N and woods E (2009)- rice husk ashl California polytechnic state university.
- [7]. Harunur ket al. (2010)- Durability of mortar in presence of rice husk ash world academy of science , engineering and technology 432010
- [8]. Abhilas.s et .al (2011)- study of the properties of concrete by partial replacement of ordinary Portland cement by rice husk ash department of civil engineering, BIT mesra ,ranchi-835215,international jornal of earth sciences and engineering ISSN 0974-5904, volume 04 , No 06 SPL,October 2011,pp 965-968.
- [9]. Kartini.K(2011)-rice husk ash pozzolanic material for sustainability-university technology MARA 40450 Shah alam , selangor
- [10]. Patnaikuni l et al (2012)- performance of rice husk ash concrete exposed to sea water 6th SASTech 2012,malaysia ,kuala lumpur .24-25march,2012.organized by khavaran institute of higher education.
- [11]. Maurice E et al .(2012)- compressive strength of concrete with rice husk ash as partial replacement of ordinary Portland cement. Department of Civil engineering, rivers state university of science and technology port Harcourt, nigeria .scholarly Journal of engineering research vol.1(2),pp.32-36,may 2012 ,ISSN 2276-8955@2012 Scholarly -journals.

- [12]. Marthon c (2012) – effect of rice husk ash (RHA) as partial replacement of cement on concrete properties.civil engineering department, shillong polytechnic, shillong,meghalaya ,india ,793008,international journal of engineering research and technology (IJERT)ISSN : 2278-0181,vol .1 Issue 6, august- 2012