

# Shear Behaviour of RCC Beam Retrofitted With Externally Bonded Basalt Textile Fabric

Sureshkumar Narayanan<sup>1</sup>, J. Kakkan<sup>2</sup>, K. N. Keerthivasan<sup>3</sup>, M. Logesh Baabu<sup>4</sup>, J. Mohamed Yasir<sup>5</sup>  
Associate Professor, Department of Civil Engineering<sup>1</sup>  
UG Students, Department of Civil Engineering<sup>2,3,4,5</sup>  
Anjalai Ammal Mahalingam Engineering College, Kovilvenni, Thiruvavur, Tamilnadu, India  
Affiliated to Anna University

## I. INTRODUCTION

- Shear on beam is defined as the internal shear stress of a beam caused by the shear force applied to the beam.
- The fiber reinforced polymer (FRP) has arisen as a promising material for shear strengthening of RCC structures due to their superior qualities such as high specific strength, better fatigue and chemical resistance.
- This resistance to sliding or resistance to forces that are parallel to the beam surface, generates a shear stress within the material.
- Basalt fiber has possessed high tensile strength, better chemical and heat resistance which is higher than that of steel fiber.
- The study finds that the beams strengthened with and without BFRP (basalt fiber reinforced polymer) strips fails in shear for L/d ratio 2.5 and the enhancement of the shear capacity of strengthened beams ranges from 5 % to 20 %.

## II. SHEAR BEHAVIOUR OF RCC BEAM RETROFITTED WITH EXTERNALLY BONDED BASALT TEXTILE FABRIC

### 2.1 Pello Larrinaga et.al investigated that

- Examining the effect of reinforced concrete slab used as a flexible reinforcing material tied out of low-grade reinforced concrete beams from ancient buildings.
- Concluding that textile has strengthened concrete in terms of increasing its flexibility and load-bearing capacity under flexure loads.

### 2.2 Faisal M. Muktar et.al investigated that

- Investigate the shear behavior and binding characteristics of ductile RC beams initially at the end of the transition to breakage breakdown failures when reinforced using a reinforced outer carbon fiber polymer (CFRP).
- The test system can serve as a bond test philosophy in the sense that this method of brittle boundary failure provides a more logical operation for crack debonding performance of FRP reinforced beams.

### 2.3 Lianheng Cai et.al investigated that

- A study of the cutting behavior of rectangular reinforced concrete (RC) reinforced CFRP grid with epoxy mortar was investigated.
- The result showed that the shear volume and split RC patterns reinforced with CFRP grid in shear can be successfully improved.

### 2.4 Yasmin Muradet.al investigated that

- To study the shear behavior of RC beams made of steel and pvc electric plastic wire fibers.
- The result of a highrise test of + 47.44% in the estimated deformity occurs when a large percentage of plastic wires are inserted into the concrete mix. Finished models are also developed into ABAQUS to mimic the numerical behavior of the templates.

**2.5 Subhrasmita Majumder et.al investigated that**

- Studying the shear strength behavior of missing reinforced concrete (RC) beams reinforced with geosynthetic materials.
- Comparing the performance of geogrid models enclosed in these parameters is better compared to closed RC geotextile beams and higher in closed specimens.
- It is guaranteed that geogrid and geotextile materials can be a very useful solution for reinforcing the RC beam by external or internal confinement at very low cost.

**2.6 Haya H.Mhanna et.al investigated that**

- Experimental study on the effect of reinforced concrete shear reinforcement (RC) T-beams with modulus carbon fiber reinforced polymer (CFRP) laminates and anchors.
- The result shows that U-wraps led to a 61 percent increase in shear strength compared to the control model, but the failure was dominated by strong bonding of CFRP laminates, with no indication of ductility before failure.

**2.7 Yasmin Muradet.al investigated that**

- Study the cutting behavior of RC beams with basalt and polypropylene fibers.
- The result shows that the inclusion of 0.6% polypropylene fibers improved shear strength, peak deviation, ductility and initial stiffness up to 23.2%, 39.74%, 195% and 2.56% with reference
- beam prepared with ordinary concrete with a concentration of 2.5% basalt fibers up to 20%, 64%, 121% and 21.2% compared to beams prepared with ordinary concrete respectively.
- The study of the parameters were the basics of WWM, location, and high temperatures and the performance of the monitored structure in terms of retention capacity, resistance, durability and durability.

**2.8 Rajai Z. AL-Rousan et.al investigated that**

- The study of the parameters were the basics of WWM, location, and high temperatures and the performance of the monitored structure in terms of retention capacity, resistance, durability and durability.
- The result showed that the embedded WWM showed significant performance in improving the cutting capacity exposed to high temperatures of RC beams, WWM is active in improving the internal shear reinforcement for the exposure of high-temperature RC beams.

**2.9 Enass Alrajfiet.al investigated that**

- Investigate the performance of the RC beam's structure made of natural composite, reconstituted composite concrete and asphalt concrete that has also been sought under normal and high temperatures.
- The result showed that the temperature had a negative impact on the shear strength, load capacity, stretch strength, and deviation of the RC beams; the increase in RAP percentage has resulted in a decrease in their carrying capacity.

**2.10 E.Ferrieret.al investigated that**

- To investigate with a flax fiber reinforced polymer (FFRP) using the external bonding method (EB) and near surface mounted method (NSM).
- The result indicates that the ultimate load increased by 10% to 35% for the reinforced beams, the shear strengthening analysis of concrete beam using a new natural material, the shear reinforcement of concrete beams.

**2.11 Kagan Sogut et.al investigated that**

- Investigate the behavior of RC T- bars reinforced with embedded FRP bars.
- Test results and FE showed that concrete and FRP contributions to shear shear and total shear strength all decreased with the increase in steel-to-FRP shear reinforcement ratio.

**2.12 Emad E.Etmanet.al investigated that**

- A test to test the shear strength of the reinforced concrete beams (RC) provided by pre-assembled steel trusses in the shear span area.
- The result showed that reinforced steel beams showed better shear performance and improved shear width compared to those reinforced beams with the same reinforced bars.

**2.13 Trung Kien Nguyenet.al investigated that**

- Investigate the behavior of the RC deep beam structure without shear reinforcement.
- The result shows a large donation of a deep rusty rod with adequate gripping capacity of beam models and a shear span-to-depth measurement and corrosion degree and corrosion degree does not always result in adverse effects in failure mode, and resistance to shear, rusty beams.

**2.14 Chalachew B.Hunegnawet.al investigated that**

- To investigate the effect of the orientation of stirrups on the shear capacity of RC beams as the shear- span-to-depth ratio.
- The results revealed that the shear capacity increases as the arrangement of stirrup changes from conventional vertical arrangement to inclined arrangement and Shear capacity also increases as concrete compressive strength increase, which shows that concrete contribution to the shear capacity of beams.

**2.15 Eric Hugheset.al investigated that**

- Equilibrium reinforced concrete slabs with basalt fiber reinforcement and reinforcing parts of the structure.
- The data show that the yield and strength of the end times of the beams have been increased and the re-installed beams also showed swelling and better performance.
- Investigate the shear reinforcement of RC beams with basalt fiber reinforced polymer (BFRP) composites.

**2.16 Swapnasarit Karet.al investigated that**

- Investigate the shear reinforcement of RC beams with basalt fiber reinforced polymer (BFRP) composites.
- The result shows that reinforced concrete load failure increases by 17-50% and the efficiency of basalt fiber sheets in increasing shear capacity to 20% higher than that of glass fiber sheets.

**2.17 Chittaranjan B.Nayak et.al investigated that**

- To investigate the structural and cracking behaviour of RC T- beams is investigated experimentally and analytically strengthened with basalt fiber reinforced polymer (BFRP).
- The result demonstrates that superficially bonded BFRP can enhance the flexural capacity and reduce the deflection of the beam and the most effective wrapping pattern was a 45° than 90° wrapping and without wrapping, it shows different cracking patterns and yield points of the beam with and without strengthening.

**2.18 Abathar Al-Hamrani et.al investigated that**

- Study the shear behavior of basalt fiber reinforced concrete (BFRC) basalt-reinforced beams and glass fiber reinforced bars of polymers and stirrups.
- The result shows that increasing the longitudinal stiffness of the BFRP-FRC beams tested by 50 and 120% led to an increase in their final strength by 24 and 48%, the carrying capacity of the BFRP-FRC tested beams decreased significantly by 46 %, Reduction of stirrups space from 250 mm to 170 mm showed a 20% increase in tested load capacity.

**2.19 Ali Saribiyik et.al investigated that**

- Experimental study on the shear strength of reinforced concrete beams (RC) with basalt fiber reinforced polymer (BFRP) composites.

- The result shows that the shear volume of RC beams reinforced with BFRP compounds increased between 43% and 100%.

**2.20 R.Madotto et.al investigated that**

- Investigate the effectiveness of BFRP in reinforcing reinforced concrete beams.
- The BFRP fabric has been shown to be effective in increasing both the shear strength and flexibility capacity of the tested beams.

**2.21 Walid Mansour et.al investigated that**

- Investigate the shear consolidation of continuous RC beams with web openings with FRP layers.
- The results showed that the continuous RC beams containing openness in the zone II group were the most affected among the analyzed areas and the group's load capacity decreased from 7.3 to 66.1% compared to the solid rod.

**2.22 Bo Wang et.al investigated that**

- To investigate the experimental results of four-point bending tests for reinforced concrete (RC) beams strengthened by carbon fiber reinforced polymer (CFRP) grids and sprayed polymer-cement-mortar (PCM).
- The result indicates that the shear strengthening effect of the CFRP grid-PCM reinforcing layers bonded along both sides of RC beams was sufficient.

**2.23 Hiroshi Sasano et.al investigated that**

- Improving plant life by allowing long-term performance, numerical model, which can detect changes in structural performance due to drying.
- The numerical method model can accurately assess the effect of drying on the members of the structure, although there are some remaining problems regarding brittle breakage.

**2.24 Omar R.Abuodeh et.al investigated that**

- To study the behavior of shear lacking reinforced concrete (RC) reinforced shear with side-bonded laminates and warped fiber-reinforced reinforced (FRP) laminates.
- The result showed that a strong neural propagating back-propagating network (RBPNN) with selected parameters was able to predict FRP severity more accurately ( $r^2 = 0.885$ ; RMSE = 8.1 kN) than that of RBPNN with the first 15 restrictions ( $r^2 = 0.668$ ; RMSE = 16.6 kN).

**2.25 Shervin K.Ghomi et.al investigated that**

- Study the seismic activity of the internal GFRP-RC column joints.
- The result shows that the linear nature of the GFRP material led to lower residual damage to the joints of the GFRP-RC column compared to its corresponding RC metal counterparts and the GFRP-RC joints with multiple cyclic loads up to 8% without drifting rate strong failure.

**2.26 Hiroshi Sasano et.al investigated that**

- A study of the performance of an older RC structure, a numerical model, taking into account the moisture transfer associated with shrinkage and the apparent changes in concrete material, is proposed.
- The result shows the distribution of rebar stress after drying, changes in diagonal fracture patterns, changes in diagonal fracture patterns, styles in load change relationships, especially with the strength of diagonal cracks.

**2.27 Ade Lisantono et.al investigated that**

- Studying the behavior of high fly fly ash cutting as replacing the Portland cement of reinforced concrete beams (RC).

- The result shows that that can be achieved by beams with 50% fly ash due to higher shaving power than 60% beam and 70% fly ash.

**2.28 C.Pellegrino et.al investigated that**

- Investigate the behavior of reinforced concrete (RC) beams reinforced with shear with external bonds.
- The result shows an increase in shear strength of reinforced beams increasing with increasing axial strength of the composite and effective problems in composite compositions using available models that were much lower than the maximum weight measured with heavy gauges placed in the composites.

**2.29 G.M.Chenet.al investigated that**

- Rate reinforced concrete (RC) beams can be reinforced with shear with reinforced polymer composites (EB) fiber reinforced fiber (FRP) by means of FRP strap straps, FRP jackets or FRP wraps.
- The analytical solution is that the development of the FRP shear contribution by opening the shear crack and investigating the shear interaction between different components (FRP shear reinforcements, steel shear reinforcements, and concrete) in RC shear reinforced beams with FRP.

**2.30 Liu Jin et.al investigated that**

- Rc cantilever seismic shear failure behavior test with opposite stiffness under load for low fatigue.
- The result shows that the alleged cutting capacity of RC cantilever beams is significantly reduced as the size of the structure increases and the shear strength indicates a stronger size effect.

**2.31 M.Breveglieri et.al investigated that**

- Imitating crack shear pressure transfer in a concrete model of crack smeared concrete is essential to accurately predict the deterioration and cracking behavior of RC elements indicating shear failure.
- The result shows that the holes are drilled with a cross section, in the desired direction, and steel or FRP wires are inserted into these holes and fastened to the concrete substrate with adhesive materials.

**2.32 Patrick Huber et.al investigated that**

- Measure the shear strength of reinforced concrete beams with a small amount and without opposite stiffening.
- The result shows that the opening of the crack and slide behavior are directly related to the shape of the critical shear crack, Although the effect of compacting is more pronounced at large fracture angles, the number of stirrups falling through the critical shear crack is reduced by beams and stirrups.
- Although crack kinematics was clearly dependent on organ depth and the presence of stirrups, especially with respect to crack opening behavior, it did not show dependence on the type of concrete regarding crack openness or slippery behavior.

**2.33 P.Bernardi et.al investigated that**

- Behavioral representation of pre- and post-fragmentary behavior using a basic model for the analysis of reinforced concrete structures.
- Experimental results show that bare concrete panels are subject to biaxial pressure, as well as RC and SFRC beams without shear reinforcement and high fracture width due to appearance and durability problems.

**2.34 Belal Almassri et.al investigated that**

- To study the key features of the FE numerical model developed using the FEMIX computer code to predict the contribution of surface-mounted polymer rods (NSM) carbon-fiber-reinforced polymer (CFRP) in the repair of RC beams of rusted concrete.
- The result shows that the efficiency of the NSM strategy is limited by the semi-conical impact of each NSM CFRP contribution of the rod and the unadulterated point span of the SB beams, which resulted in the appearance of cracks in the center. RC beams are fastened to the shaft.

**2.35 R.Siva Chidambaram et.al investigated that**

- Exploratory studies are being conducted to evaluate the feasibility of geo-grid as an additional cutting edge in RC beam models.
- The result shows that significant improvements in the strength and post-harvest behavior of wooden models depend on%% reinforced concrete and the use of geo-grid sealing and the proper use of geo-grid reinforced concrete not only., helps to achieve ductile behavior but also transforms brittle failure mode.

**2.36 Lei Wang et.al investigated that**

- Investigate the shear behavior of rusty concrete (RC) beams with stirrups and inclined bars.
- It shows that the slightest loss of rust less than 10% on stirrups and sloping bars has little effect on the deformity of the shaft and rust of stirrups and sloping bars does not change the mode of shear pressure compression failure.

**2.37 Christian Escrig et.al investigated that**

- Studying reinforced concrete beams cut with a variety of reinforced mortar.
- The result suggests that the effectiveness of the reinforcement systems is limited by the performance of the TRM matrix bond with the concrete or substrate or by reinforcing fabric and comparisons between different TRM composites.
- It can be said that PBO fabrics (PXM750) showed excellent performance, increasing shear resistance as well as the flexibility of the reinforced beams, even on a non-linear stage.

**2.38 A.Deifalla et.al investigated that**

- In this study, a set of new experiments that were able to mimic the behavior of T-shaped curves under a combined shear and torsion was developed.
- The result shows that the flange stirrup is most effective in resisting the torsion moment over shear force, the amount of torque to the shear ratio significantly affects the behavior of the T-shaped beams modified according to the fracture pattern; failure mode; strut angle of inclination; cracking and final torque; post-cracking rigidity of torsional; fractures and high shear; flange and web stirrup strain.

**2.39 G.Sakar et.al investigated that**

- Experimental and numerical testing response to reinforced concrete (RC) loading concrete shear with Glass Fiber Reinforced Polymer (GFRP) rods using a nearby surface mounted (NSM) method.
- The result shows that the NSM GRRP screening program tested significantly improved the carrying capacity of the tested samples between 49% and 66%.
- The ductility of the reinforced samples was more than that it controls the unconfirmed template and varies between 112% and -172% and increase GFRP web size from 6 mm to 10 mm and reduce space from 160 mm to 120 mm.

**2.40 Georges EL-Saikalyet.al investigated that**

- Measure the fatigue performance of RC T-beams reinforced shavings to increase service load using pre-made CFRP L-shaped lamps.
- The results confirmed the possibility of using CFRP L-shaped laminates to extend the service life of RC T-beams dealing with fatigue loading and the presence of flexible steel in reinforced beams led to a significant reduction in shear resistance due to CFRP, which ensures interchangeability between steel and steel-CFRP.

**2.41 Omar A.Farghal et.al investigated that**

- Study the performance of shear reinforced concrete (RC) T-beams reinforced shear with a combination of Carbon Fiber Reinforced Polymer (CFRP).

- The result shows that reinforced beams can survive cycles of cyclic loading cycles (= 50% of very heavy load) without obvious signs of damage (premature failure) indicating the effectiveness of the CFRP reinforcement program in increasing the fatigue of structural fatigue and reinforced beams provided with U-jacket authorized sheets. An acceptable enhancement in structural ductility.

**2.42 Sherif H.AL-Terasawy et.al investigated that**

- Study the performance of reinforced concrete (RC) beams reinforced beams.
- The result shows that CFRP folding that is tied to the outside has improved the cutting ability significantly and that the customized CFRP configuration is more effective than vertical.

**2.43 Joaquim A.O. BARROS et.al investigated that**

- The Experimental research has demonstrated the excellent performance of the near surface mounted (NSM) technique with carbon fiber reinforced polymer (CFRP) laminates for the shear strengthening of reinforced concrete (RC) beams.
- The result shows that the NSM laminates provided a large increase in terms of load carrying capacity after shear crack formation and the effectiveness level of the NSM technique was limited by the concrete tensile strength, Inclined laminates were more effective than vertical laminates and an increase of the percentage of laminates led to an increase of the shear capacity of the beams.

**2.44 Sherif H.AL Tersawyet.al investigated that**

- To analyze the performance of reinforced concrete (RC) beams strengthened in shear.
- The result indicates that externally bonded CFRP wraps enhanced the shear strength of beams significantly and that inclined CFRP configuration is more effective than vertical ones.

**2.45 Jiangfeng Dong et.al investigated that**

- Experimental research on reinforced concrete (RC) beams with external flexural and flexural–shear strengthening by fiber reinforced polymer (FRP) sheets consisting of carbon FRP (CFRP) and glass FRP (GFRP).
- The output shows that the flexural–shear strengthening arrangement is much more effective than the flexural one in enhancing the stiffness, the ultimate strength and hardening behavior of the RC beam.

**2.46 Abdeldjelil Belarbi et.al investigated that**

- Investigate the shear behavior of reinforced concrete slabs (RC) reinforced with fiber-reinforced polymer (FRP) composites.
- The result showed that the increase in shear strength from about 23% to 26% compared to the corresponding control rod, FRP-reinforced beams with mechanical anchorage showed 7-48% higher shear strength than beams, FRP strengthens full shear- RC scale poles work just as well as those seen in low-level RC beams.

**2.47 H.K.Lee et.al investigated that**

- Investigate the behavior and performance of reinforced concrete (RC) deep T-section beams reinforced with CFRP sheets.
- The test result shows that important variables of reinforcing length, combination of fiber direction, and anchorage have a significant impact on the performance of the hardened reinforcing beams.

**2.48 Xiao-Hui Wanget.al investigated that**

- An experimental investigation in the effect of corrosion damaged partial length in one shear span on the shear behaviour and load capacity of reinforced concrete (RC) beams.
- The result indicate that the mechanical behaviour and load capacity of the test specimens are greatly influenced by the bond characteristics and high corrosion induced damage within the partial length.

**2.49 Mark G.Stewart et.al investigated that**

- To consider that the spatial and time dependent variability of pitting corrosion, structural resistance and load effects.
- The result indicates that the probability of failure assuming brittle reinforcement behaviour is up to 450% higher than assuming ductile behaviour.

**2.50 Andrea Rizzo et.al investigated that**

- Estimate the shear strengthening of reinforced concrete (RC) members is the use of near-surface mounted (NSM) fiber-reinforced polymer (FRP) reinforcement.
- The result shows shear strengthening of reinforced concrete (RC) members is the use of near-surface mounted (NSM) fiber-reinforced polymer (FRP) reinforcement the stiffer bond slip behavior of the joints induced larger peak bond stresses and accelerated the initiation debonding cracks in the concrete, the reduced distance between the bars accelerated the formation of a debonding failure pattern involving all the bars together.

**REFERENCES**

- [1]. Pello Larrinaga, Leire Garmendia, Carlos Chastre, Jose-Tomas San-Jose, "Low-grade RC beams strengthened with TRM composite based on basalt, carbon and steel textiles: Experimental and analytical study" Case Studies in Construction Materials -2022.
- [2]. Faisal M.Muktar, Mohamed E.Shehadah, "Shear behavior of flexural CFRP-strengthened RC beams with crack- induced delamination: Experimental investigation and strength model" composite structures-2021.
- [3]. Lianheng Cai, Qian Liu, Rui Guo, "Study on shear behavior of RC beams strengthened by CFRP grid with epoxy mortar" Composite structures-2021.
- [4]. Yasmin Murad, Haneen Abdel-jabar, "Shear behavior of RC beams made with plastic and steel wires: Experimental and numerical study" Case studies in Construction materials-2021.
- [5]. Subhrasmita Majumder, Showmen Saha, "Shear behavior of RC beams strengthened using geosynthetic materials by external and internal confinement" structures-2021.
- [6]. Haya H.Mhanna, Rami A.Hawileh, Jamal A.abdalla, "Shear behavior of RC T-beams externally strengthened with anchored high modulus carbon fiber-reinforced polymer(CFRP) laminates" Composite structures-2021.
- [7]. Yasmin Murad, Haneen Abdel-Jabbar, "Shear behavior of RC beams prepared with basalt and polypropylene fibers" Case studies in construction materials-2021.
- [8]. Rajai Z. AL-Rousan, "The behavior of heated damaged shear-deficient RC beams reinforced internally with welded wire mesh" Case studies in construction materials-2021.
- [9]. Enass Alrajfi, Ahmed M.Ashteyat, Yasmin Z. Murad, "Shear behavior of RC beams made with natural, recycled aggregate concrete and reclaimed asphalt aggregates under normal and elevated temperature" Journal of Building Engineering-2021.
- [10]. E.Ferrier, L. Michel, M.D.Ngo, "Experimental study on the shear behavior of RC beams reinforced by natural composite materials (flax fibers)" Structures-2021.
- [11]. Kagan Sogut, Samir Dirar, Marios Theofanous, Asaad Faramarzi, Amar Nath Nayak, "Effect of transverse and longitudinal reinforcement ratios on the behavior of RC T- beams Shear-strengthened with embedded FRP bars" Composite structures-2021.
- [12]. Emad E.Etman, Hamdy M.Afefy, Ahmed T.Baraghith, Mohammed Abuelwafa , "Shear behavior of RC beams reinforced with internal trussed steel strips at shear span zone" structures-2021.
- [13]. Trung Kien Nguyen, Ngoc Tan Nguyen, "Finite element investigation of the shear performance of corroded RC deep beams without shear reinforcement" Case studies in Construction Materials-2021.
- [14]. Chalachew B.Hunegnaw, Temesgen W.Aure , "Effect of orientation of stirrups in combination with shear span to depth ratio on shear capacity of RC beams" Heliyon-2021.
- [15]. Eric Hughes, Sreekanta Das, Niel Van Engelen, David Lawn, "Concrete girders retrofitted with basalt fiber fabric – A feasibility study using lab tests and field application" Engineering Structures-2021.

- [16]. Swapnasarit Kar, K.C.Biswal, "External shear strengthening of RC Beams with basalt fiber sheets: An experimental study" Structures-2021.
- [17]. Chittaranjan B.Nayak, Giridhar N.Narule, Harashwardhan R.Surwase, "Structural and cracking behaviour of RC T-beams strengthened with BFRP sheets by experimental and analytical investigation" Journal of King Saud University-Engineering Sciences-2021.
- [18]. Abathar Al-Hamrani,Wael Alnahhal, "Shear behavior of basalt FRC beams reinforced with basalt FRP bars and glass FRP stirrups : Experimental and analytical investigations" Engineering Structures-2021.
- [19]. Ali Saribiyik, Bassel Abodan, Muhammed Talha Balci, "Experimental study on shear strengthening of RC beams with basalt FRP strips using different wrapping methods" Engineering Science and Technology, an International Journal-2020.
- [20]. R.Madotto, N.C.Van Engelen, S.Das, G.Russo, M.Pauletta, "Shear and flexural strengthening of RC beams using BFRP fabrics" Engineering Structures-2020.
- [21]. Walid Mansour, "Numerical analysis of the shear behavior of FRP-Strengthened continuous RC beams having web openings" Engineering Structures-2020.
- [22]. Bo Wang, Zhengpeng Wang, Kimitaka Uji, Junlei Zhang, Rui Guo, "Experimental investigation on shear behavior RC beams strengthened by CFRP grids and PCM" structures-2020.
- [23]. Hiroshi Sasano, Ipeei Maruyama, "Numerical study on the shear failure behavior of RC beams subjected to drying" Nuclear Engineering and Design-2019.
- [24]. Omar R.Abuodeh, Jamal A.Abdalla,Rami A.Hawileh, "Prediction of shear strength and behavior of RC beams strengthened with externally bonded FRP sheets using machine learning techniques" Composite structures-2019.
- [25]. Shervin K.Ghomi, Ehab El-Salakawy, "Effect of joint shear stress on seismic behavior of interior GFRP –RC beam-column joints" Engineering structures-2019.
- [26]. Hiroshi Sasano, Ipeei Maruyama, "Numerical study on the shear failure behavior of RC beams subjected to drying" Nuclear Engineering and Design-2019.
- [27]. Ade Lisantono, Haryanto Yoso Wigroho, Roy Arnol Purba, "Shear behavior of high -volume fly ash concrete as replacement of Portland cement in RC beam" Procedia Engineering-2017.
- [28]. J.H.Gonzalez-Libreros, L.H.Sneed, T.D Antino, C.Pellegrino, "Behavior of RC beams strengthened in shear with FRP and FRCM composites" Engineering structures-2017.
- [29]. G.M.Chen, S.W.Li, D.Fernando, J.F.Chen, "Full-Range FRP failure behaviour in RC beams shear-strengthened with FRP Wraps" International journal of solids and structures-2017.
- [30]. Liu Jin, Xiuli Du, Dong Li, Xiao Su, "Seismic behavior of RC Cantilever beams under low cyclic loading and size effect on shear strength: An experimental characterization" Engineering structures-2016.
- [31]. M.Breviglieri, J.A.O.Barros, A.Aprile, A.Ventura-gouveia, "Strategies for numerical modeling the behavior of RC beams strengthened in shear using the ETS technique" Engineering structures-2016.
- [32]. Patrick Huber,Tobias Huber,Johann Kollegger, "Investigation of the shear behavior of RC beams on the basis of measured on the basis of measured crack kinematics" Engineering Structures-2016.
- [33]. P.Bernardi, R.Cerioni, E.Michelini, A.Sirico, "Numerical modeling of the cracking behavior of RC and SFRC shear-critical beams" Engineering Fracture Mechanics-2016.
- [34]. Belal Almassri, Joaquim A.O.Barros, Firas Al Mahmoud, Raoul Francois, "A FEM-based model to study the behaviour of corroded RC beams shear-repaired by NSM CFRP rods technique" Composite structures-2015.
- [35]. R.Siva Chidambaram, Pankaj Agarwal, "Flexural and shear behavior of geo-grid confined RC beams with steel fiber reinforced concrete" Construction and building materials-2015.
- [36]. Lei Wang, Xuhui Zhang, Jianren Zhang, Yafei Ma, Yongming Liu, "Effects of stirrup and inclined bar corrosion on shear behavior of RC beams" Construction and building materials-2015.
- [37]. Christian Eserig, Lluís Gil, Ernest Bernat-Maso, Francesc Puigvert, "Experimental and analytical study of reinforced concrete beams shear strengthened with different types of textile-reinforced mortar" Construction and Building Materials-2015.

- [38]. A.Deifalla,A.Ghobarah, “Behavior and analysis of inverted T-Shaped RC beams under shear and torsion” Engineering structures-2014.
- [39]. G.Sakar, R.A.Hawileh, M.Z.Naaser, J.A.Abdulla, M.Tanarlan, “Nonlinear behavior of shear deficient RC beams strengthened with near surface mounted glass fiber reinforcement under cyclic loading” Materials and design-2014.
- [40]. Georges EL-Saikaly, Omar Chaallal, “Fatigue behavior of RC T-beams strengthened in shear with EB CFRP L-shaped laminates” Composites: Part B-2014.
- [41]. Omar A.Farghal, “Fatigue behavior of RC T-beams strengthened in shear with CFRP sheets” Ain Shams Engineering Journal-2014.
- [42]. Sherif H.AL-Terasawy, “Effect of fiber parameters and concrete strength on shear behavior of strengthened RC beams” Construction and building materials-2013.
- [43]. Joaquim A.O. BARROS, Hadi Baghi, Salvador J.E.Dias, A.Ventura-Gouveia, “A FEM-based model to predict the behaviour of RC beams shear strengthened according to the NSM technique” Engineering structures-2013.
- [44]. Sherif H.Al Tersawy, “Effect of fiber parameters and concrete strength on shear behavior of strengthened RC beams” Construction and building materials-2013.
- [45]. Jiangfeng Dong, Qingyuan Wang, Zhongwei Guan, “Structural behavior of RC beams with external flexural and flexural- shear strengthening by FRP sheets” Composites: part B-2012.
- [46]. Abdeldjelil Belarbi, Sang-Wook Bae, Antonio Brancaccio, “Behavior of full-scale RC T-beams strengthened in shear with externally bonded FRP sheets” Construction and building materials-2011.
- [47]. H.K.Lee, S.H.Cheong, S.K.Ha, C.G.Lee, “Behavior and performance of RC T-section deep beams externally strengthened in shear with CFRP Sheets” Composite structures-2010.
- [48]. Xiao-Hui Wang, Xiang-Hua Gao, Bing LI, Bao-Ru Deng, “Effect of bond and corrosion within partial length on shear behaviour and load capacity of RC beam” Construction and building materials-2010.
- [49]. Mark G.Stewart, “Mechanical behavior of pitting corrosion of flexural and shear reinforcement and its effect on structural reliability of corroding RC beams” Structural Safety-2008.
- [50]. Andrea Rizzo, Laura De Lorenzis, “Behavior and capacity of RC beams strengthened in shear with NSM FRP reinforcement” Construction and building materials-2007.